Ferotec Friction Ltd

D3806 Product Data Sheet

General Description

D3806 is a closely woven, semi-flexible friction material. It is based on yarn spun from a blend of glass and synthetic fibres together with a fine copper wire to enhance its strength and heat dissipation properties. The impregnant has been specially developed to give it good frictional properties combined with a good degree of flexibility. It has a high coefficient of friction and performs well in wet and damp environments which makes it particularly suited for marine applications. To help during fitting to brake shoes and bands it can be softened and made more pliable by warming in a bonding oven to between 150 & 180°C for sufficient time for the heat to penetrate the fabric.

<u>Applications</u>

Industrial drum and band-brakes Industrial clutches Marine towing winches Miscellaneous industrial devices

Bonding

D3806 may be bonded using any of the established adhesives recommended for friction material. However, to obtain the best results it is necessary to use a thermosetting adhesive.

Mating Surface

A good quality, fine grained, pearlitic cast iron or cold rolled steel with a Brinell hardness of 180. Cast steels are not recommended.

Availability

| Ro | 511 | |
|----|-----------------------|-------------------|
| Le | ngth | 10 Metres |
| W | idth | 20 to 510mm |
| Th | ickness range | 3.2mm to 20mm |
| Sh | eet size 1000mm v 660 | mm v 4 8 to 16 om |

Sheet size 1000mm x 660mm x 4.8 to 16.0mm thick

Linings and special shapes on request

| | TECHNICAL DATA | | | |
|---|--|---|--------------------------------|------|
| Initial Bedding Characteristics | Friction μ for design purposes : | Static (cold) Dynamic | 0.45 0.42 | |
| C2 C2 C2 C1 C2 | Recommended Operating Range Pressure Max. rubbing speed Max. continuous temperature | Dynamic Static 25 m/s 110°C | 70-860 kN/m² 70-2,410 kN/m² | |
| Pressure Sensitivity | Max. intermittent temperature Max. temperature | 180°C 225°C | | |
| 0.6 0.6 0.5 0.4 0.2 0.1 0 0.5 1 1.5 2 2.5 3 3.5 4 Unit Pressure (MVm ²) | Test Conditions Application Speed Clamping pressure Average temperature Average temperature PHYSICAL PROPERTIES | 15m/s o.61 MN/m ³ (88.5 ibf/in ²) Initial Bedding 140°C Pressure Sensitivity / Speed Sensitivity 80°C | | 80°C |
| Speed Sensitivity | Density | 1.20 g/cc | | |
| 0.6 | Ultimate tensile strength | 24.0 MN/m² (3,500 i | bf/in²) | |
| | Ultimate compressive strength | 100.0 MN/m² (14,500 ibf/in²) | | |
| 0.1 | Ultimate shear strength | 17.2 MN/m² (2,500 it | of/in²) | |
| 0 5 10 15 20 25 30 | Rivet holding capacity | 61.8 MN/m² (9,000 i | bf/in²) | |
| Speed (m/s) | Thermal conductivity | 0.79 W/m °C | | |

(All physical properties shown above are all mean values)

The information supplied in this data sheet is believed to be accurate and reliable, and was obtained by scientific and laboratory testing. However, since actual conditions of use are largely outside the control of FEROTEC FRICTION LIMITED, it is suggested that this material be thoroughly tested and its suitability for use be determined before final acceptance.

Issue 5 Jun 10

Ferotec Friction Ltd Unit C Greenfield Business Park, Bagillt Rd, Holywell, Flintshire CH8 7HJ, United Kingdom Tel: +44 1352 710360 Fax: +44 1352 719368 E-mail: ffsales@ferotecfriction.co.uk Website: www.ferotecfriction.com